

INDOFIL SOFT SPF-01

Anionic Synthetic Fatliquor

Indofil Soft SPF-01 is anionic synthetic softener with high penetration & excellent light fastness. It is & suitable for all kind of leather articles.

PHYSICAL PROPERTIES:

Composition	: Anionic synthetic aliphatic softeners.
Appearance	: Yellow to Yellow brown clear to slight hazy viscous Liquid.
pH (1:10)	: 6.0 – 8.0
Stability of Emulsion	: Stable to mild acids, alkalis, hard water & electrolytes .

DISCRIPTION:

Indofil Soft SPF-01 is anionic specialty lightfast synthetic fatliquor especially designed for all types of Shoe uppers, softies, garment nappa, gloving and milled leathers. It is lightfast and has capacity to penetrate & drive all other fatliquors throughout the cross section of leathers.

Indofil Soft SPF-01 imparts following unique characteristics,

- Good anionic penetrative fatliquor.
- Imparts good softness with light weight & fiber opening.
- Imparts smooth surface touch & warm handle.
- Lightfast hence suitable for white & pastel shades.
- Helps in uniform distribution of retanning agents and fatliquors.
- Compatible with all retannage, vegetable extracts & fatliquors.
- No dye bleaching effect

APPLICATION:

Indofil Soft SPF-01 is recommended for all types of full grain, corrected grain uppers, suede, gloving and milled articles. It can be added to the drum after pre dissolved with water.

Indofil Soft SPF-01 is having a very fine emulsion hence most suitable for thicker leather articles due to its high penetration properties.

Indofil Soft SPF-01 is having wide range of applications as follows,

For Cow/Buff full grain & corrected grain : 3% – 5% in fatliquoring with other fatliquors.

For Nappa and gloving leathers : 4% – 10% in fatliquoring with other fatliquors.

For suede & nubuck leathers : 4% – 8% in fatliquoring with other fatliquors

For upholstery leathers : 6% – 10% in fatliquoring with other fatliquors

STORAGE STABILITY: 6-9 months if properly stored in cool & dry place under shed in sealed drums.

Please stir well the product before every use.

Technical Suggestions are without any obligation

Prepared on 02-06-2016 (SPCD/Leather/ SPF-01/June 2016/FL/Rev. 0)